

DATE:

SPECIFICATION SHEET NO:

DESCRIPTION:

PSA

158

BLOC PUR 2.00MM

JUNE 2023

ARCHITECTURAL SPECIFICATIONS / BOQ

SPECIFICATION:

Supply and install Bloc PUR single solid colour with a textured emboss, flexible PVC sheet flooring in 2.00mm thickness, shall have the following laminated construction: 0.7mm pigmented homogeneous PVC wear layer, with a 1.30mm PVC backing featuring a pimple emboss, shall incorporate a specially formulated polyurethane reinforcement, as with any plain material, the soil hiding properties are less than similarly coloured patterned floors, the frequency of a regular and well planned maintenance regime should be considered at the outset to ensure the plain floorcovering retains the optimum appearance, careful consideration should be given when choosing very light colours in highly trafficked areas, the use of a robust and effective dirt barrier system should be considered early in the specification chain, in accordance with EN ISO 10582/EN 649, the in-use classification must be at least 23/34/43 as described in EN ISO 10874: i.e. domestic areas with intense use; commercial areas with very heavy traffic; and heavy light industrial areas, in respect of flame spread, the flooring shall have been fully tested to EN13501-1 and certified as having Class Bfl-S1, the Binder Content shall be Type I as defined in EN ISO 10582, this product does not accumulate static charge sabove 2kV and is classified as 'antistatic' when tested to EN1815. For specialist applications where there is a requirement to dissipate the electrostatic charge see the Polyflor ESD product ranges, with regards the European requirement EN 13893 for slip resistance, the flooring shall be classified DS, making it suitable for use in areas which are predominantly dry. When tested to DIN 51130 the product shall be classified as R10. For safety flooring with sustainable wet slip resistance, refer to the Polysafe ranges, in respect of light fastness, the flooring shall have been fully tested to ISO 105-BO2 Method 3 as having a pass to ≥6, the flooring must be available in 2.01 metre width, including a 0.01 metre selvage for on-site trimming, to minimise the

Colour:

Code:

INSTALLATION: (PLEASE NOTE: ALWAYS USE COMPATIBLE PRODUCTS FROM ONE SUPPLIER)

Please note the following: Due to extreme temperature fluctuations in South Africa and Africa, we DO NOT recommend the method of cold welding. Polyflor SA recommends hot welding of heterogeneous products.

On receipt of rolls:

>>Check that colours correspond to those ordered, that quantities are correct and that there is no damage.

>>In particular, check that rolls are from one batch, if that was requested on the order.

>>On arrival at site, the rolls should be safely secured in an upright position; (2m widths only) and stored, together with the adhesive, at a minimum temperature of 18°C for at least 24 hours before laying. Rolls delivered horizontally on pallets/skids should be decanted and stored upright immediately upon acceptance of delivery. Leaving rolls laid horizontally on pallets more than 24 hours following delivery can cause compression problems. Claims cannot be accepted for damage to rolls where they have been stored horizontally on pallets/skids more than this time period. To ensure a successful installation all Polyflor products should be correctly acclimatised.

>>To achieve best results, site conditions should be as described in BS 8203 or prevailing local/national standards. A working temperature of between 18°C and 27°C is required for at least 48 hours prior to, and during, the installation period; and for 24 hours afterwards. Conditioning should be carried out in the same room or areas as the installation, to prevent thermally induced dimensional changes.

>>Inflammable adhesives require special storage conditions. Contact the adhesive manufacturer or see current literature for details.

PRIOR TO INSTALLATION WHERE UNDERFL OOR HEATING IS USED

>>The system should be fully tested and commissioned prior to the flooring installation commencing.

>>Underfloor heating systems should be switched off and be fully cooled for a minimum of 48 hours prior to the installation commencing. The system should remain off and fully cooled during the installation and for a minimum of 48 hours afterwards. It should then be slowly brought back up to the working temperature incrementally over several days.

>>A maximum subfloor temperature; (at the adhesive line) of 27°C should never be exceeded. Specialist high temperature adhesives should be used in areas with underfloor heating, direct sunlight, and areas of high solar gain. Please refer to the Polyflor Approved Adhesive List or contact your adhesive manufacturer for more information.

>>When underfloor heating is the only source of heat, alternative measures must be taken to meet all site condition requirements, as previously mentioned.

SPECIALIST FLOORING & WALL PROTECTION PARTNER

Tel: 011 609 3500|Email: <u>marketing@polyflor.co.za</u> | www.polyflor.co.za Poly Sales House, 8B Buwbes Road North, Sebenza, 1609, South Africa. PO Box 3967, Edenvale, 1610, South Africa



PREPARATION OF WORK AREA

The work area should now be prepared to receive the sheet flooring.

>>Ensure that all other trades have completed their work and removed all their equipment and materials.

>>Remove all debris and vacuum the whole subfloor area.

>>Check the condition of the subfloor and make good as necessary.

>>Stone or power grind any cementitious subfloor to remove any 'nibs' or ridges.

>>Remove any surface contaminants, which may affect adhesion. Sweep or vacuum again prior to laying.

>>If required by the contract, or if in doubt, check the moisture content of the subfloor and record the results and method used. Good lighting is essential.

>>It is important to note that commencement of work is deemed by many as acceptance of the site conditions as suitable for laying floor coverings.

LAYOUT OF SHEET

>>The architect may have provided a drawing showing the direction in which the material should be laid. In this case, lay the sheet as directed. >>Where the architect has left the direction to the discretion of the flooring contractor; at the tender stage show in which direction the material will be laid and state that your estimate is based on this.

>>Always pay particular attention to where seams will fall, avoiding such occurrences as seams in the centre of doorways.

>>If large windows are installed, minimise the effect of the joints by laying towards the window.

SLABBING THE SHEET

>>Polyflor recommends that all Polyflor sheet flooring be rolled out face upward, taking care not to damage the surface, and cut approximately to size.

>>Allowance of at least 100mm should be made at the ends for trimming in, the slabs should then be left overnight for 24 hours to condition at a minimum temperature of 18°C.

>>If it is not feasible to 'lay out' the slabbed sheet overnight, back roll the product and allow to stand for 15 minutes prior to the installation. Failure to do this will result in shrinkage as back rolling will occur when 'folding back' to adhere to subfloor.

FITTING THE FIRS T LENGTH

>>Place the first sheet in position next to the wall with the outer edge approximately 15mm from the nearest point.

>>Adjust the lie of the sheet so that the inner edge is parallel with the axis of the room (fig. 1).

>>Depending upon the depth of the recesses, use either a bar scriber or a pair of scribers to trace the profile of the wall. The scribers should be set to allow for the deepest recess or rake of the wall. Holding the scribers square to the edge, trace the wall profile onto the face of the sheet. With this method, all irregularities of the wall will be accurately reproduced onto the surface of the sheet. If the scribed line

is difficult to see due to the colour or decoration, rub suitably contrasting chalk dust into the line to highlight it.

>>Ease the sheet away from the wall and, using a hook blade trimming knife, cut off the excess material to the scribed line. Slide the sheet back against the wall and check the fit, making any minor adjustments as necessary.

>>When satisfied that the fit on the first edge is correct, use a pencil to trace the opposite edge onto the subfloor (line A-B).

>>In the centre of the room, draw a line on both the sheet and subfloor square to the main axis of the sheet (line C-D).

>>Keeping the inner edge of the sheet on line A-B, slide the sheet back to clear the wall at one end of the room.

>>Set the scribers to the distance now between lines C and D. Trace the end wall profile and cut to fit as described earlier. >>Repeat for the other end of the sheet. Once completed, the whole sheet – when slid back into position – should fit the wall profiles exactly.

FITTING SUBSE QUENT LENGTHS

>>Place the second length parallel to the first length, with a minimum of 25mm overlap along the adjoining edges or overlap of selvedge. >>On the opposite side, trace the edge along the whole length onto the subfloor. In the middle, draw a line C-D at right angles to the main axis, as previously described.

>>Using the longitudinal line as a guide, slide back the sheet from the end wall and fit as described in Section 3.6.

>>Repeat for the opposite end.

>>Repeat the sequence for all remaining lengths.

>>On the final length, which abuts the opposite wall, fit as described for the first length.

ALIGNMENT OF DE CORATION (HETEROGENEOUS RANGES ONLY)

This type of floor covering features a print layer with a regular, repeat decoration (e.g., wood plank). With wood effect designs: >>To maximise the final appearance of the installation and to ensure the decorative effect is not lost, it is important that care is taken to align the decoration of each adjacent sheet.

>>The edge of the printed plank can be used in the lengthwise direction as a guide. The label and printed information on the backing of the sheet must be checked and the product reverse laid when instructed.

CUTTING IN THE SEAMS

Polyflor recommends that all Polyflor sheet floor coverings are welded. Trimming off the factory edges and seam cutting is a prerequisite to enable successful grooving and welding. Note: The seams should be cut before the adhesive is applied.

ADHERING THE SHEET

Use of the correct adhesives is of paramount importance for the installation to be successful. In areas subjected to direct sunlight or extremes/fluctuations in temperatures, Polyflor always recommends the use of an approved polyurethane, epoxy, or suitable high temperature adhesive. Polyflor provides this information only as guidance. The legal responsibility for the supply and performance is that of the adhesive manufacturer. Prior to adhering the sheet, it is important to read and understand the adhesive manufacturer's instructions, recommendations, and safety advice. You need to know the hazards and limitations of the adhesive, especially the open time.

>>Spread the adhesive using a suitable trowel to the manufacturer's recommendations ensuring that the correct notch size is maintained throughout the installation. If the notch shows signs of wear the trowel should be renewed immediately.

>>If pressure sensitive adhesive is used the resultant serrated adhesive edges should be flattened with a lambswool roller pre-wetted with adhesive.

>>Never spread more adhesive than can be laid within the open time.

Polyflor does not recommend any method of adhesive application, such as spraying, which cannot guarantee the spread rate. >>After each section has been laid, except for the perimeter, thoroughly roll the sheet in both directions with a 68kg articulated floor roller. Repeat for each section until the main field of sheet has been laid.

>>When spreading dispersion-based adhesives on impervious or non-porous bases; (including bases where a surface applied damp proof membrane or moisture vapour suppressant has been applied) it is important to apply a suitable smoothing compound of not less than 3mm thickness. Failure to apply the correct depth of smoothing compound can result in moisture becoming trapped between the sheet and the impervious or non-porous base. This can ultimately lead to failures in the adhesive bond and in some cases discolouration of the vinyl sheet products.

>>The smoothing underlayment or adhesive supplier will provide details on which product(s) within their range should be used to suit the end use application and subfloor construction, and where applicable details of which primer should be used.

>>Adhesive selection should be based on both the floor covering, substrate type and site conditions. Always select an adhesive from the Polyflor Approved Adhesive list. If in doubt about adhesive choice, please contact Polyflor on (011) 609 3500 or marketing@polyflor.co.za

MAINTENANCE: NOTE: NEVER USE A BLACK PAD TO SCRUB A PUR COATED FLOOR

To maximize efficiency of the cleaning system and minimize costs taking advantage of the Polyflor PUR-polyure than reinforcement cross linked and UV cured finish, the following is recommended:

1.Post Installation:

•All loose dirt such as dust, grit, sand etc. must be removed, preferably by vacuuming the floor.

•The floor should then be cleaned using a neutral detergent, diluted as per the manufacturer's instructions, machine scrubbed and dirty cleaning solution wet vacuumed off the floor. (If a wet vacuum is not available, a mop and wringer system can be used).

•Adhesive can be removed with an appropriate detergent/solution such as Polyflor Powerclean if necessary. As a principle, aggressive solvents should be avoided as these may affect the PUR finish. More powerful detergents such as PRO-INOX (previously Resinox) from Industroclean can be used to remove persistent soiling which is not removed by the initial clean.

•The floor should then be rinsed until all traces of the neutral detergent are removed and wet vacuumed to remove all traces of water.

2.Daily

•Sweep/mop using a disposable cloth system such as the Masslinn system or vacuum to remove dust and grit; (Ensure that the vacuum is fitted with a Hepa filtration system in a healthcare environment)

•Spot or damp mop where required using a neutral detergent such as PROCLEAN.

3.Interim or Weekly Clean (Depending on conditions)

•To remove light scuff marks:

Dry buff with a +- 1000 rpm ultra-high speed burnisher using a clean 3M pink eraser or white pad.

•To remove heavy scuff marks:

Scrub with a low speed burnisher and neutral detergent, Proclean-diluted 100ml: 10Lwith cold water using the green Eco Brilliance pad.

4. Periodically (3-9 monthly) depending on conditions

•If required, scrub with a +- 165 rpm machine fitted with a red or blue pad using neutral detergent PROCLEAN diluted 20:1 with cold water as appropriate. Rinse well with clean water and dry buff with white pad to restore finish.

Please note that all PVC welding rod is not coated. We recommend the application of a layer of PUR sealer to all welds in a PUR sheeting floor to enhance maintenance procedures.

NB: to create a higher sheen on the floor, use a 1000 rpm machine using a clean white 3M pad or green Eco Brilliance Pad.

This program will keep maintenance costs to a minimum and requires no sealers.

Sufficient entrance or barrier matting is highly recommended and will greatly ease the maintenance programme.





Suitable for both cold and hot welding - see installation details for more information.

 $w^{l_{T}} * weld \mbox{rod} \quad MCS = Natural Colour System \quad LRV = Light Reflectance Value \label{eq:mbox}$





bloc

Featuring a single solid colour with a textured emboss, Polyflor Bloc PUR has a 0.70mm pigmented homogeneous PVC wear layer. A high performance, heavy duty heterogeneous sheet floorcovering with a polyurethane reinforcement, Bloc ts ideally suited for use within the retail, letsure and commercial sector. The quality of a finished installation of Bloc is dependent upon the preparation of the subfloor which must be smooth. Also the frequency of a regular and well planned maintenance regime should be considered at the outset to ensure the plain floorcovering retains the optimum appearance.



POLYFLOR

EN 428/150 24346 Gauge 2.0mm Wear Layer EN 429/150 24340 0.70mm Roll Size EN 426/ISO 24341 2m x 20m = 40m² Total Weight EN 430/ISO 23997 2660g/m EN 649 150 10582 General Performance Ø Use Area EN 685/ISD 10874 80 Resistance to Chemicals EN 423/ISO 2698 Good resistance Class BR-ST EN 1350H1 ASTM E048 2 Reaction to Fire Clara 1 CAN/ULC SIDE 2 PSV < 300; 50V < 500 Group T B Abrasion Resistance EN 649 Binder Content EN 150 10582 Type I EN 13873 Class DS Slip Resistance* DIN 5030 R10 150 243431 \$0.10mm \$P Residual Indentation ASTM1970 (Modifie 0.125mm (750 ps)) Castor Chair (continuous use) EN 425/ISO 4918 Suitable EN 434/ISD 23999 **Dimensional Stability** \$0,40% Placbilly EN 435/150 24344 (Method A) Pass 20mm d Underfloor Heating Suitable, max 27°C 3 Static Electrical Propenalty EN 1875 \$ 2.0kV Classified as 'antrotatic' Light Pastness 150105-802 (Method 3) 26 Indoor Air Comfort GOLD FloorScore Eurofins certified product Certified 996 VOC Emissions Ag88/ABG Finnish MI Pain Certified Responsible Sourcing BES BOOK Excellent Environmentally Preferable Flooring - PolyRor Bloc FUR achieves BRE Global Environmental A+ rating (certificate No. ENF-405) in major use areas such as education and healthcare and is Green Tag LCA Robe certified with GreenBale level A - Silver Plus, Generic EN ISB04 Environmental Product Declaration (EPD) available on request. If is 100% recyclable. Recyclable via the Recofloor scheme. Visit were polyfloccom/subtanability PUR - Polyfiar Bloc PUR features a high quality, creas linked polyurethane reinforcement, UV cured to provide a low-cost, polish free maintenance regime For the lifetime of the flooring. As with any plain material, the sol hiding properties are less than similarly coloured patterned floors. Higher frequency of maintenance may be required to ensure optimum appearance. Careful consideration should also be given when choosing very light colours in highly trafficient areas. The use of a robust and effective dirt barrier system should be considered early in the specification stage. Hygiene - All Polytion commercial sheet vitryl ranges provide a continuous, impervious and hygienic flooring solution which can be confidently cleaned in accordance with recommended maintenance procedures and approved maintenance products. The implementation of an effective cleaning regime is the most important defence against infection. 爱 For information and advice regarding handling and installation, adhesives, tailored maintenance, applications, chemical maintance and product warranty, consult Polyflor Customer Technical Services on +44 (0)601 767 7912, or email tech/Tpolyflor.com. *flar safety flooring with sustainable with sign resistance, refer to Polysafe ranges. The data prevented is correct at the time of printing. For tailor information, please visit our website polyfloccom. Decoration and shade may vary slightly from the samples shown. 🏧 🔵 🚢 🙎 🔘 🍳 CE POLYFLOR UK Sales Direct: +44 (0)/617671122 | Export Sales Direct: +44 (0)/617671913 James Haldend Sample Requests: +44 (0)(6) 767 2551 | email: info@polyflor.com | www.polyflor.com

Octuber 2020